



FICHA TÉCNICA / DATA SHEET

TARPAULIN		
COMPOSITION / COMPOSICIÓN		100% PVC
WIDTH / ANCHO		250 CM
WEIGHT IN M ² / PESO EN M ²		750 g/m ² ± 5%
THICKNESS / ESPESOR	DIN 53352	52 µm
BASE THREAD DENSITY / DENSIDAD DEL HILO BASE	DIN 53350	1000×1000 D (DENIER)
BASE FABRIC DENSITY / DENSIDAD DEL TEJIDO BASE	DIN 53351	20×20 HILOS/PULGADA
BREAK STRENGTH WARP / RESISTENCIA A LA ROTURA (URDIMBRE)	GB/T1040	2500 N/5 CM
BREAK STRENGTH WEFT / RESISTENCIA A LA ROTURA (TRAMA)	GB/T1040	2200 N/5 CM
TEAR STRENGTH WARP / RESISTENCIA AL DESGARRO (URDIMBRE)	DIN 53363	280 N/5 CM
TEAR STRENGTH WEFT / RESISTENCIA AL DESGARRO (TRAMA)	DIN 53363	250 N/5 CM
ADHESION / ADHESIÓN	DIN 53357	90 N/5 CM
TEMPERATURE RANGE / RANGO DE TEMPERATURA	DIN 53368	30 ~+ 70°C
FLAME RETARDANCY / RETARDANCIA AL FUEGO	AUTOEXTINGUIBL E / SELF- EXTINGUISHING	-